

Niretan B F25

Polyamide 6, reinforced with 25% of glass fibre for injection moulding.

	Properties	Test condition	Method	Unit	Value
Mechanical	Tensile Stress at Break	5 mm/min	ASTM D638	MPa	155/90
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	210/130
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	7000/4000
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	90/120
	Izod Notched Impact Strength	-20°C/3mm	ASTM D256	J/m	60/100
	Rockwell Hardness		ASTM D785	R-scale	115/100
	Elongation	50 mm/min	ASTM D638	%	3,5/7
Thermal	Heat Distortion Temperature H.D.T	1.82 MPa	ASTM D648	°C	200
	Linear Expansion Co-efficient	23°C/55°C	ISO 11359-2	10 ⁻⁵ K ⁻¹	4
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	650
	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Electrical	Relative Permittivity	1 Mhz – dry	IEC 60250	-	3,8/4,2
	Dissipation Factor	1 Mhz – dry	IEC 60250	-	0,02/0,12
	Dielectric Strength	S=1 mm	IEC 60243-1	KV/mm	34/24
	Surface Resistivity	dry	IEC 60093	□	10 ¹⁴ /10 ¹³
	Volume Resistivity	dry	IEC 60093	□ □ cm	10 ¹⁵ /10 ¹²
Various	Moulding Shrinkage	parallel	-	%	0,4/0,8
Physical	Density	23°C	ASTM D792	g/cm ³	1,33

	Properties	Test condition	Method	Unit	Value
					7
	Humidity Absorption from Atmosphere	23°C – 50% HR	ASTM D570	%	2,5
	Cristalline Melting Temperature	DSC	-	°C	220

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delievery.