

M33AG8A

Data Sheet

- Glass fiber(40%) reinforced grade

Physical Properties		Test Method	Unit	Value
Density		ASTM D792	g/cm ³	1.55
Moisture Absorption	23°C, 50%RH	ASTM D570	%	0.30
Mold Shrinkage	3mm, MD/TD	ASTM D955	%	0.2/1.0
Mechanical Properties		Test Method	Unit	Value
Tensile Strength at Yield	23°C	ASTM D638	MPa	150
Elongation at Break	23°C	ASTM D638	%	4
Flexural Strength	23°C	ASTM D790	MPa	200
Flexural Modulus	23°C	ASTM D790	MPa	8,500
Charpy Notched Impact strength	23°C	ISO 179/1eA	kJ/m ²	12
Thermal Properties		Test Method	Unit	Value
Melting Temperature		ASTM D3418	°C	222
Melt Flow Index	240°C, 2.16kg	ASTM D1238	g/10min	12
Flammability	t = 0.8mm	UL 94	Class	HB

DISCLAIMER : The information contained in this data sheet is based on our current knowledge and experience. This information is based on only above-mentioned product produced in HYOSUNG CORPORATION through relevant test methods and conditions and does not relate to any products made of this product with the inclusion of other additives, such as processing aids or colorants. This information should not be construed as a promise or guarantee of specific properties of this product described or its suitability for a particular application, so users make their own determination as to its suitability to their purposes prior to use this product. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of this product. HYOSUNG makes no warranty and assumes no liability in connection with any use of this information.