

M730F

Data Sheet

- Very low flow, Food contact grade (Natural)

Physical Properties		Test Method	Unit	Value
Density		ASTM D792	g/cm ³	1.24
Water Absorption	23°C, 50%RH	ASTM D570	%	0.5
Mold Shrinkage	3T, MD/TD	ASTM D955	%	2.2/2.1

Mechanical Properties		Test Method	Unit	Value
Tensile Strength at Yield	23°C	ASTM D638	MPa	58
Nominal Strain at Break	23°C	ASTM D638	%	300
Flexural Strength	23°C	ASTM D790	MPa	48
Flexural Modulus	23°C	ASTM D790	MPa	1,200
Charpy Notched Impact strength	23°C	ISO 179/1eA	kJ/m ²	19

Thermal Properties		Test Method	Unit	Value
Melting Temperature		ASTM D3418	°C	222
Heat Deflection Temperature	18.6 Kg/cm ²	ASTM D648	°C	105
Melt Flow Index	240°C, 2.16kg	ASTM D1238	g/10min	3
Flammability	t = 0.8mm	UL 94	Class	HB

Properties are subject to change with a new knowledge and development.

DISCLAIMER : The information contained in this data sheet is based on our current knowledge and experience, so it may change as new knowledge and experience becomes available. This information is based on only above-mentioned product produced in HYOSUNG CORPORATION through relevant test methods and conditions and doesn't relate to any products made of this product with the inclusion of other additives, such as processing aids or colorants. This information should not be construed as a promise or guarantee of specific properties of this product described or its suitability for a particular application, so users make their own determination as to its suitability to their purposes prior to use this product. It is the sole responsibility of the users to investigate whether any existing patents are infringed by the use of this product. HYOSUNG makes no warranty and assumes no liability in connection with any use of this information.