

## ISO Property | LOTTE Advanced Materials

| INFINO. | Grade      | EF-1032 |
|---------|------------|---------|
|         | Resin Type | PC/ABS  |

Flame Retardant, Miscellaneous

| ltem  | Measuring Method | Condition                       | Unit              | Value |
|---|------------------|---------------------------------|-------------------|-------|
|   |                  | Physical                        |                   |       |
| Specific Gravity                            | ISO 1183         | Natural or representative color | -                 | 1.19  |
| Melt Flow Index                             | ISO 1133         | 250℃, 10kg                      | g/10min           | 20    |
|   |                  | Mechanical                      |                   |       |
| Tensile Strength at Yield                   | ISO 527          | 50mm/min                        | MPa               | 65    |
| Tensile Strain at break                     | ISO 527          | 50mm/min                        | %                 | 73    |
| Tensile Modulus                             | ISO 527          | 50mm/min                        | MPa               | 2400  |
| Tensile Strength at break                   | ISO 527          | 50mm/min                        | MPa               | 55    |
| Flexural Strength                           | ISO 178          | 2mm/min                         | MPa               | 95    |
| Flexural Modulus                            | ISO 178          | 2mm/min                         | MPa               | 2400  |
| Izod Impact Strength (notched)              | ISO 180 1A       | at 23°C, 4mm                    | KJ/m <sup>2</sup> | 53    |
| Charpy Impact Strength (V-<br>notched)      | ISO 179 1eA      | at 23°C, 4mm                    | KJ/m <sup>2</sup> | 62    |
| Rockwell Hardness                           | ISO 2039-2       | R-scale                         | -                 | 120   |
|   |                  | Thermal                         |                   |       |
| Heat Deflection<br>Temperature(Unannealed)  | ISO 75-2         | 1.8MPa, 4.0mm                   | °C                | 92    |
| Heat Deflection<br>Temperature (Unannealed) | ISO 75-2         | 0.45MPa, 4.0mm                  | °C                | 101   |
| VICAT Softening Temperature                 | ISO R 306        | B/50                            | °C                | 107   |
| VICAT Softening Temperature                 | ISO R 306        | B/120                           | °C                | 129   |
|   |                  | Flammability                    |                   |       |
| Flammability                                | UL94             | V-0                             | mm                | 1.5   |

<sup>1.</sup> The value above is the representative value of the NP or representative color and may have deviation. It can only be used for selecting materials.

Information inserted in this document such as data, statements, representative values, etc. are provided solely for customer convenience. It does not expressly or impliedly guarantee anything regarding the safety or practicability of the (1) materials, (2) products, and/or (3) design that utilizes recommendations or proposals, of LOTTE Advanced Materials. Furthermore, nothing in the contents of this document shall have any legal binding effect, and especially, the representative value is simply for reference and is not a minimum value that has legal binding effect.

Whether materials and/or products of LOTTE Advanced Materials and/or a design that uses or utilizes LOTTE Advanced Materials' recommendations or proposals are (is) compatible with individual uses shall be determined solely by each user and such user shall be solely responsible for any results, including but not limited to, any and all loss and damages incurred due to such uses. Users must implement and verify all testing and analyses for proving the safety and compatibility of final products that have been created or altered by using LOTTE Advanced Materials' materials or products. The data and values inserted and/or contained in this document may be changed due to quality improvement of the product without any prior notification.

\* The last update date : 05/13/2014

<sup>2.</sup> The value above shall not be regarded as a material specification and cannot be used for molding designs.