

Infino WP-1100

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,22
	Melt Flow Index	250°C, 2,16kg	ISO 1133	g/10min	40
	Mold Shrinkage	-	ISO 2577	%	0.3-0.5
Mechanical	Charpy Impact Strength (notched)	4mm	ISO 179 1eA	KJ/m ²	12
	Stress at Yield	50mm/min	ISO 527	Kg/cm ²	92
	Flexural Strength	2mm/min	ISO 178	Kgf/cm ²	150
	Flexural Modulus	2mm/min	ISO 178	Kgf/cm ²	4,7
Thermal	Heat Deflection Temperature	18.56kgf/cm ²	ISO 75-2	°C	119

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.