

Infino WP-1200

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,28
	Mold Shrinkage	-	ISO 2577	%	0.2-0.4
	Melt Flow Index	250°C, 2,16kg	ISO 1133	g/10min	35
Mechanical	Tensile Strength	50mm/min	ISO 527	MPa	109
	Flexural Strength	2,8mm/min	ISO 178	MPa	187
	Flexural Modulus	2,8mm/min	ISO 178	MPa	7.400
	Charpy Impact Strength (notched)	4mm	ISO 179 1eA	KJ/m ²	11
Thermal	Heat Deflection Temperature	18.56kgf/cm ²	ISO 75-2	°C	119

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delievery.