

Infino SC-1102UR

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,2
	Mold Shrinkage (MD)	Flow at 3,2mm(MD)	ISO 2577	%	0,5-0,7
	Water Absorption	23°C	ISO 62	%	0,2
	Melt Flow Index	300°C, 1,2kg	ISO 1133	g/10min	11,5
Mechanical	Tensile Strength at Yield	50mm/min	ISO 527	MPa	65
	Flexural Strength	2mm/min	ISO 178	MPa	92
	Flexural Modulus	2mm/min	ISO 178	MPa	2300
	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	80
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m ²	85
	Rockwell Hardness	R-scale	ISO 2039-2	-	120
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	125
	Vicat Softening Temperature	B/50	ISO R 306	°C	145
Flammability	Flammability	V-2	UL94	mm	0,8-2,5
Optical	Transmissivity	3mm	ISO D13468	%	89
	Haza	3mm	ISO D13468	%	0,2

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.