

Infino TK-2046HM

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,61
	ASH Content	-	ISO 3451	%	40,5
	Melt Flow Index	300°C, 1,2kg	ISO 1133	g/10min	20
Mechanical	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	3
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m ²	2,8
	Flexural Strength	2,8mm/min	ISO 178	MPa	800
	Flexural Modulus	2,8mm/min	ISO 178	MPa	77000
	Tensile Strength at Yield	5mm/min	ISO 527	MPa	620
	Tensile Strain at Break	5mm/min	ISO 527	%	1,5
	Izod Impact Strength (unnotched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	16
	Charpy Impact Strength (unnotched)	at 23°C, 4mm	ISO 179 1eA	KJ/m ²	13
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	250
Appearance	Yellowness Index	3,2mm	ASTM D1925	-	4

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.