

HiPrene MR71SE

| | Properties | Test condition | Method | Unit | Value |
|------------|----------------------------------|----------------|--------------------|-------------------|-------|
| Physical | Melt Mass-Flow Rate | | ISO 1133-2/A | g/10min | 40 |
| | Specific Gravity | | ISO 1183 | g/cm ³ | 1 |
| Mechanical | Tensile Strength | 23° C | ISO 527-2/1A/50 | MPa | 15 |
| | Nominal Tensile S-train at Break | 23° C | ISO 527-2/1A/50 | % | 25 |
| | Flexural Modulus | 23°C | ISO 178/B | MPa | 1300 |
| Impact | Notched Izod Impact Strength | 23°C | ISO 180/A | KJ/m ² | 35 |
| Thermal | Volatile Matters | | GS Standard SOP003 | % | <0,12 |
| | Ash Content | 600°C | ISO 3451-1/A600°C | % | 15 |

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delievery.