

Ecoblend S85 Nero

- Lega PC/ABS industriale caratterizzata da elevate proprietà termiche e da un ottimo bilancio modulo / impatto
- Grado sviluppato per lo stampaggio ad iniezione.

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	260°C / 5 kg	ASTM D1238	g/10min	15-25
Mechanical	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	75
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	2300
	Rockwell Hardness	23°C	ASTM D785	M-scale	115
	Izod Notched Impact Strength	23°C/3,2 mm	ASTM D256	J/m	>420
Thermal	Vicat Softening Temperature	9,8N / 120°C/h	ASTM D 1525	°C	>137
	Linear Expansion Coefficient	23°C/55°C	ISO 11359-2	10 ⁻⁶ K ⁻¹	7
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	650
	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Various	Density		ASTM D792	g/cm ³	1,16
	Humidity Content at Equilibrium	23°C / 50 % U.R.	ISO 62	%	0,2
	Moulding Shrinkage	parallel	-	%	0,4-0,8

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delievery.