

Niplene C30

Polypropylene homopolymer, filled with 30% calcium carbonate, for the injection moulding of items of medium hardness and good aesthetical surface.

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	230 °C / 2,16 Kg	ASTM D1238	g/10min	10
Mechanical	Tensile Stress at Yield	50 mm/min.	ASTM D638	MPa	20
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	45
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	2800
	Rockwell Hardness		ASTM D785	R-scale	105
	Izod Notched Impact Strength	23°C/3,2 mm	ASTM D256	J/m	30
	Elongation	50 mm/min	ASTM D638	%	60
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	110
	Heat Distortion Temperature H.D.T	1.82 MPa	ASTM D648	°C	65
Various	Density		ASTM D792	g/cm ³	1,12
	Moulding Shrinkage	parallel	-	%	0,8-1,4

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.