

Niplene T20 FR V0

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	230 °C / 2,16 Kg	ASTM D1238	g/10min	9
Mechanical	Tensile Stress at Yield	50 mm/min.	ASTM D638	MPa	25
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	50
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	3400
	Rockwell Hardness		ASTM D785	R-scale	86
	Izod Notched Impact Strength	23°C/3,2 mm	ASTM D256	J/m	30
	Elongation	50 mm/min	ASTM D638	%	50
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	116
	Heat Distortion Temperature H.D.T	1.82 MPa	ASTM D648	°C	90
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	960
	UL 94 Rating	S=1.6 mm	UL 94	class	V2
	UL 94 Rating	S=3.2 mm	UL 94	class	V0
Various	Density		ASTM D792	g/cm ³	1,32
	Humidity Content at Equilibrium	23°C / 50 % U.R.	ISO 62	%	0,3
	Moulding Shrinkage	parallel	-	%	0,4-0,8

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.