

Niplene F40 AGR

Polypropylene homopolymer, reinforced with 40% glass fibre chemically coupled to the polymeric matrix

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	230 °C / 2,16 Kg	ASTM D1238	g/10min	3
Mechanical	Rockwell Hardness		ASTM D785	R-scale	115
	Tensile Modulus	5 mm/min	ISO 527-I/-2	MPa	9200
	Tensile Stress at Break	5 mm/min	ISO 527-I/-2	MPa	98
	Elongation	5 mm/min	ISO 527-I/-2	%	3
	Flexural Maximum Stress	1,3 mm/min	ISO 178	MPa	150
	Flexural Elastic Modulus	1,3 mm/min	ISO 178	MPa	7600
	Izod Notched Impact Strength	23°C	ISO 180/A	KJ/m ²	12
	Izod Notched Impact Strength	-20°C	ISO 180/A	-	8,5
	Tensile Stress at Break	5 mm/min	ASTM D638	MPa	105
	Thermal	Linear Expansion Coefficient	23°C/55°C	ISO 11359-2	10 ⁻⁵ K ⁻¹
Vicat Softening Temperature (unannealed)		B/50	ISO 306	°C	138
Heat Distortion Temperature (unannealed)		A - 1.80 MPa	ISO 75A-I/-2	°C	150
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	650
	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Electrical	Relative Permittivity	1 Mhz - dry	IEC 60250	-	2,7
	Dissipation Factor	1 Mhz - dry	IEC 60250	-	0,001

	Properties	Test condition	Method	Unit	Value
					60
	Surface Resistivity	dry	IEC 60093	□	10 ¹⁴
	Volume Resistivity	dry	IEC 60093	□ □ cm	10 ¹⁵
Various	Humidity Content at Equilibrium	23°C / 50 % U.R.	ISO 62	%	0,1
	Moulding Shrinkage	parallel	-	%	0,15-0,55
	Moulding Shrinkage	transversal	-	%	0,25-0,75
	Density		ISO 1183	g/cm ³	1,22

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.