

Niretan B F15 M

Polyamide 6, reinforced with 15 % of glass fibre, impact modified, for injection moulding

	Properties	Test condition	Method	Unit	Value
Mechanical	Tensile Stress at Break	5 mm/min	ASTM D638	MPa	100
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	145
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	4500
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	90
	Rockwell Hardness		ASTM D785	R-scale	100
	Elongation	50 mm/min	ASTM D638	%	3,7
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	205
	Heat Distortion Temperature H.D.T	1.82 MPa	ASTM D648	°C	175
	Linear Expansion Co-efficient	23°C/55°C	ISO 11359-2	10 ⁻⁵ K ⁻¹	6
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	650
	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Electrical	Surface Resistivity	dry	IEC 60093	Ω	10 ¹⁴ /10 ¹³
	Volume Resistivity	dry	IEC 60093	Ω cm	10 ¹⁵ /10 ¹²
Various	Moulding Shrinkage	parallel	-	%	0,5/1,0
Physical	Density	23°C	ASTM D792	g/cm ³	1,21
	Humidity Absorption from Atmosphere	23°C – 50% HR	ASTM D570	%	2,5
	Cristalline Melting Temperature	DSC	-	°C	220

Properties

Test condition

Method

Unit

Value

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.