

Niretan B SV15

	Properties	Test condition	Method	Unit	Value
Mechanical	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	3000
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	90
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	195
Physical	Density	23°C	ASTM D792	g/cm ³	1,22

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.