

Infino NH1015V

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,17
	Melt Flow Index	220°C, 10kg	ISO 1133	g/10min	30
Mechanical	Tensile Strength at Yield	50mm/min	ISO 527	MPa	61
	Tensile Strain at Break	50mm/min	ISO 527	%	45
	Tensile Modulus	50mm/min	ISO 527	MPa	2500
	Tensile Strength at Break	50mm/min	ISO 527	MPa	48
	Flexural Strength	2mm/min	ISO 178	MPa	89
	Flexural Modulus	2mm/min	ISO 178	MPa	2550
	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	14
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m ²	17
	Rockwell Hardness	R-scale	ISO 2039-2	-	118
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	82
	Heat Deflection Temperature (unannealed)	0.45 MPa, 4.0mm	ISO 75-2	°C	94
	Heat Deflection Temperature (annealing)	1.8 MPa, 4.0mm	ISO 75-2	°C	97
	Heat Deflection Temperature (annealing)	0.45 MPa, 4.0mm	ISO 75-2	°C	102
	Vicat Softening Temperature	B/50	ISO R 306	°C	100
	Vicat Softening Temperature	B/120	ISO R 306	°C	103
	RTI, Ele	1.5 ,V-0	UL746B	°C	90
	RTI, Imp	1.5 ,V-0	UL746B	°C	85
	RTI, Str	1.5 ,V-0	UL746B	°C	90
Flammability	Flammability	V-0	UL94	mm	1,5



Properties	Test condition	Method	Unit	Value
				2

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.