

Infino XP-2130A

	Properties	Test condition	Method	Unit	Value
Physical	Specific Gravity	Natural or Representative Color	ISO 1183	-	1,63
	Mold Shrinkage (MD)	Flow at 3.2mm(MD)	ISO 2577	%	0,3-1,2
	ASH Content	-	ISO 3451	%	31
	Water Absorption	23°C	ISO 62	%	0,02
	Melt Flow Index	316°C , 5kg	ISO 1133	g/10min	120
Mechanical	Izod Impact Strength (notched)	at 23°C, 4mm	ISO 180 1A	KJ/m ²	11
	Charpy Impact Strength (V-notched)	23°C, 4mm	ISO 179 1eA	KJ/m ²	11
	Rockwell Hardness	R-scale	ISO 2039-2	-	116
	Flexural Strength	2,8mm/min	ISO 178	MPa	190
	Flexural Modulus	2,8mm/min	ISO 178	MPa	10200
	Tensile Strength at Yield	5mm/min	ISO 527	MPa	139
	Tensile Strain at Break	5mm/min	ISO 527	%	3
Thermal	Heat Deflection Temperature (unannealed)	1.8 MPa, 4.0mm	ISO 75-2	°C	275
Flammability	Flammability	HB	UL94	mm	0,75
	Flammability	V-0	UL94	mm	0,75
Electrical	Dielectric Constant	-	IEC 60250	10EΛ6HZ	4
	Dielectric Loss Tangent	-	IEC 60250	10EΛ6HZ	0,002
	Volume Resistivity	-	IEC 60093	□ □ cm	10□16

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.