

Niblend F817

- PC-ABS

alloy reinforced with 17 % of glass fibre

- **Grade for injection**

moulding, characterized by very high heat resistance, high stiffness and easy processing

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	260°C / 5 kg	ASTM D1238	g/10min	10
Mechanical	Tensile Stress at Yield	50 mm/min.	ASTM D638	MPa	5600
	Tensile Stress at Break	5 mm/min	ASTM D638	MPa	70
	Elongation at Break	50 mm/min	ASTM D638	%	2
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	115
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	4800
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	90
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	138
	Ball Pressure Test	125°C	IEC 60695-10-2	-	Pass
	Linear Expansion Coefficient	parallel	ISO 11359-2	cm/cm/°C	0,000030
	Linear Expansion Coefficient	transversal	ISO 11359-2	cm/cm/°C	0,000080
Flame Behaviour	UL 94 Rating	S-1.6 mm	UL 94	class	HB
	UL 94 Rating	S-3.2 mm	UL 94	class	HB
Electrical	Dissipation Factor	1 Mhz - dry	IEC 60250	-	0,0085

	Properties	Test condition	Method	Unit	Value
					35
	Surface Resistivity	dry	IEC 60093	Ω	10 ¹⁶
	Volume Resistivity	dry	IEC 60093	Ω cm	10 ¹⁴
Various	Density		ASTM D792	g/cm ³	1,27
	Humidity Content at Equilibrium	23°C / 50 % U.R.	ISO 62	%	0,05
	Moulding Shrinkage	parallel	-	%	0,2-0,4
	Moulding Shrinkage	transversal	-	%	0,3-0,5

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.