

Niblend S85

PC-ABS alloy of very high termic resistance, suitable to meet the ball pressure test at 125 °C

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	260°C / 5 kg	ASTM D1238	g/10min	18
Mechanical	Tensile Stress at Yield	50 mm/min.	ASTM D638	MPa	55
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	75
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	2300
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	500
	Izod Notched Impact Strength	-20°C/3mm	ASTM D256	J/m	150
	Rockwell Hardness	23°C	ASTM D785	M-scale	118
	Elongation	50 mm/min	ASTM D638	%	30
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	138
	Heat Distortion Temperature H.D.T	1.82 MPa	ASTM D648	°C	127
	Linear Expansion Coefficient	23°C/55°C	ISO 11359-2	10 ⁻⁵ K ⁻¹	7
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	650
	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Electrical	Relative Permittivity	1Mhz - dry	IEC 60250	-	2,9
	Dissipation Factor	1Mhz - dry	IEC 60250	-	0,05
	Dielectric Strength	S=1 mm	IEC 60243-1	KV/mm	25
	Surface Resistivity	dry	IEC 60093	Ω	10 ¹⁵
	Volume Resistivity	dry	IEC 60093	Ω cm	10 ¹⁵
Various	Density		ASTM D792	g/cm ³	1,17
	Humidity Content at Equilibrium	23°C / 50 % U.R.	ISO 62	%	0,2



Properties	Test condition	Method	Unit	Value
Moulding Shrinkage	parallel	-	%	0,4 - 0,8

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.