

# Niblend S65F UV Nero905

PC-ABS alloy characterized by good heat resistance, good flow, and easy processing. Grade for injection moulding, particularly indicated for automotive industry.

	Properties	Test condition	Method	Unit	Value
Rheological	Melt Flow Index	260°C / 5 kg	ASTM D1238	g/10min	20
Mechanical	Tensile Stress at Yield	50 mm/min.	ASTM D638	MPa	50
	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	80
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	2300
	Rockwell Hardness	23°C	ASTM D785	M-scale	116
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	550
	Izod Notched Impact Strength	-20°C/3mm	ASTM D256	J/m	150
	Elongation	50 mm/min	ASTM D638	%	>50
	Tensile Modulus	50 mm/min	ASTM D638	MPa	2350
Thermal	Vicat Softening Temperature	49N / 120°C/h	ASTM D 1525	°C	
		1.82 MPa	ASTM D648	°C	110
		23/55 °C	ISO 11359-2	10 <sup>-5</sup> K <sup>-1</sup>	8
		S=2.0 mm	IEC 695-2-12	°C	650
Heat Distortion Temperature H.D.T					
Coef. Dilatazione Termica Lineare					
Glow Wire Temperature (G.W.T)					
Flame Behaviour	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Electrical	Dielectric Strength	S=1 mm	IEC 60243-1	KV/mm	25
	Relative Permittivity	1 Mhz = secco	IEC 60250	-	2,9
	Dissipation Factor	1 Mhz = secco	IEC 60250	-	0,05

	Properties	Test condition	Method	Unit	Value
	Surface Resistivity	secco	IEC 60093	Ω	10 <sup>15</sup>
	Volume Resistivity	secco	IEC 60093	Ω cm	10 <sup>15</sup>
Various	Density		ASTM D792	g/cm <sup>3</sup>	1,12
	Humidity Content at Equilibrium	23°C / 50 % U.R.	ISO 62	%	0,2
	Moulding Shrinkage	parallel	-	%	0,5-0,8

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.