

Niplene F20

Polypropylene homopolymer, reinforced with 20% glass fibre. Standard quality.

| | Properties | Test condition | Method | Unit | Value |
|-----------------|-----------------------------------|------------------|-------------|----------------------------------|------------------|
| Rheological | Melt Flow Index | 230 °C / 2,16 Kg | ASTM D1238 | g/10min | 2 |
| Mechanical | Tensile Stress at Break | 5 mm/min | ASTM D638 | MPa | 60 |
| | Flexural Maximum Stress | 1,3 mm/min | ASTM D790 | MPa | 80 |
| | Flexural Elastic Modulus | 1,3 mm/min | ASTM D790 | MPa | 4200 |
| | Rockwell Hardness | | ASTM D785 | R-scale | 105 |
| | Izod Notched Impact Strength | 23°C/3,2 mm | ASTM D256 | J/m | 60 |
| | Izod Notched Impact Strength | -20°C/3,2 mm | ASTM D256 | J/m | 40 |
| | Elongation | 50 mm/min | ASTM D638 | % | 5 |
| Thermal | Vicat Softening Temperature | 49N / 120°C/h | ASTM D 1525 | °C | 125 |
| | Heat Distortion Temperature H.D.T | 1.82 MPa | ASTM D648 | °C | 144 |
| | Linear Expansion Coefficient | 23°C/55°C | ISO 11359-2 | 10 ⁻⁵ K ⁻¹ | 4 |
| Flame Behaviour | Glow Wire Temperature (G.W.T) | S=2.0 mm | IEC 695-2-1 | °C | 650 |
| | UL 94 Rating | S=1.6 mm | UL 94 | class | HB |
| | UL 94 Rating | S=3.2 mm | UL 94 | class | HB |
| Electrical | Relative Permittivity | 1 Mhz - dry | IEC 60250 | - | 2,7 |
| | Dissipation Factor | 1 Mhz - dry | IEC 60250 | - | 0 |
| | Dielectric Strength | S=1 mm | IEC 60243-1 | KV/mm | 60 |
| | Surface Resistivity | dry | IEC 60093 | Ω | 10 ¹⁴ |
| | Volume Resistivity | dry | IEC 60093 | Ω cm | 10 ¹⁵ |

| Properties | Test condition | Method | Unit | Value |
|---------------------------------|------------------|--------|------|---------|
| | | | | 1,04 |
| Humidity Content at Equilibrium | 23°C / 50 % U.R. | ISO 62 | % | 0,2 |
| Moulding Shrinkage | parallel | - | % | 0,4-0,8 |
| Moulding Shrinkage | transversal | - | % | 0,5-1,0 |

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.