

Niretan B F30 M2

Polyamide 6 reinforced with 30% of glass fibre, impact modified, for injection moulding.

Material available also with heat stabilisation. (SC)

	Properties	Test condition	Method	Unit	Value
Mechanical	Flexural Maximum Stress	1,3 mm/min	ASTM D790	MPa	175/110
	Flexural Elastic Modulus	1,3 mm/min	ASTM D790	MPa	6600/4200
	Izod Notched Impact Strength	23°C/3mm	ASTM D256	J/m	230/380
	Elongation	50 mm/min	ASTM D638	%	4/8,5
	Tensile Modulus	5 mm/min	ASTM D638	MPa	8000/5000
	Tensile Stress at Break	5 mm/min	ASTM D638	MPa	135/90
Thermal	Heat Distortion Temperature H.D.T	1.82 MPa	ASTM D648	°C	200
	Linear Expansion Coefficient	23°C/55°C	ISO 11359-2	10 ⁻⁵ K ⁻¹	4
Flame Behaviour	Glow Wire Temperature (G.W.T)	S=2.0 mm	IEC 695-2-1	°C	650
	UL 94 Rating	S=1.6 mm	UL 94	class	HB
	UL 94 Rating	S=3.2 mm	UL 94	class	HB
Electrical	Relative Permittivity	1 Mhz – dry	IEC 60250	-	3,8/4,2
	Dissipation Factor	1 Mhz – dry	IEC 60250	-	0,02/0,12
	Dielectric Strength	S=1 mm	IEC 60243-1	KV/mm	34/24
	Surface Resistivity	dry	IEC 60093	Ω	10 ¹⁴ /10 ¹³
	Volume Resistivity	dry	IEC 60093	Ω cm	10 ¹⁵ /10 ¹²
Various	Moulding Shrinkage	parallel	-	%	0,25/0,6
Physical	Density	23°C	ASTM D792	g/cm ³	1,3
	Water Absorption	24h - 23°C	ASTM D570	%	6,6

	Properties	Test condition	Method	Unit	Value
	Humidity Absorption from Atmosphere	23°C – 50% HR	ASTM D570	%	2,1
	Cristalline Melting Temperature	DSC	-	°C	220

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.