

# MAXIMID 7550GF/PA.MXD6

MAXIMID 7550GF is a glass fiber 50%-reinforced MXD6-PA grade.

It is suitable for automotive, electrical & electronics, and consumer parts.

	Properties	Test condition	Method	Unit	Value
Physical	Density		ISO 1183	g/cm <sup>3</sup>	1,65
	Filler contents		ISO 4351	%	50
	Molding Shrinkage (Flow Direction)	t 3mm, Ø 100mm	KEP Method	%	0,2-0,3
	Water absorption	23°C, 50% RH	ISO62	%	0,17
Thermal	Melting Point		DSC	°C	238
	Heat Deflection Temperature (HDT)	1,8MPa	ISO75	°C	232
	Flammability	t=0,8mm	UL94	Class	HB
	Coefficient of linear thermal expansion		ISO 11359	10 <sup>-5</sup> /°C	1,7
Mechanical	Tensile Strength		ISO 527	MPa	295
	Strain at Break		ISO 527	%	2,0
	Flexual Strength		ISO 178	MPa	400
	Flexual Modulus		ISO 178	MPa	18500
	Charpy Notched Impact Strength		ISO 179/IeA	kJ/m <sup>2</sup>	11,5
Electrical	Surface Resistivity		IEC 60093	Ω	3*10 <sup>16</sup>
	Volume Resistivity		IEC 60093	Ω cm	10 <sup>16</sup>
	Dielectric Strength		IEC 60243-1	kV /mm	18
	Permittivity	100Hz	IEC60250		4,5
	Permittivity	1MHz	IEC60250		4,7
	Dissipation Factor	100Hz	IEC60250		0,098
	Dissipation Factor	1MHz	IEC60250		0,024
Processing	Pre-Drying	4 - 8 h	Dehumidified Dryer	°C	90-120



Properties	Test condition	Method	Unit	Value
Molding (Barrel) Temperature	3-zone screw		°C	250-280
Mold Temperature			°C	120-140

All values are approximate values and are given after the best knowledge and conscience. Hence, because of variable processing terms or processing procedures an obligation cannot be derived from it.

Tekuma Kunststoff GmbH is not the manufacturer of a.m. product. The information return the result of the quality inspection. An assurance of certain properties and qualities for specify uses cannot be derived. We recommend additional tests with regard to the suitability ability. Guarantee occurs within the scope of our general terms of sale and terms of delivery.